


Product Datasheet

Longridge Sandstone

Sourced from Cumbrian Stone Ltd



Honed Ashlar



Rock Faced Ashlar



Typical Variations and Inclusions

- Shade Variations
- Orange Swirls
- Clay Holes
- Iron Markings
- Gritty Inclusions
- Dark Spots/Shadows

Quarry Location

Longridge Sandstone is quarried from the following quarry:

Leeming Quarry (Longridge)
Stonyhurst, Lancashire
operated by Brown Bros (Longridge) Ltd.

as published in the Directory of Mines and Quarries 2020 by the British Geological Survey.

Please note that printed colours may vary from printer to printer therefore the images contained within this datasheet are for reference purposes only. We would always recommend obtaining a physical sample for colour matching purposes. Large display panels of all of our materials available to view at our Penrith showroom, and we are happy to supply a sample of any of our products on request and at the point of order.

The variations shown are indicative of the features that can be found within this material/product. It is not possible to guarantee that any of the features shown will be present in any given stone, nor is it possible to guarantee the exclusion of any of these features. More information on the variations and range of inclusions commonly found within this product can be found at www.cumbrianstone.co.uk



Cumbrian Stone Ltd
Montal Place
Stalker Road
Gilwilly Industrial Estate
Penrith, Cumbria
CA11 9FE

sales@cumbrianstone.co.uk
Tel: 01768 867867
www.cumbrianstone.co.uk

Product Datasheet

Longridge Sandstone

Sourced from Cumbrian Stone Ltd



Production Information

Longridge Stone is a hard-wearing medium to coarse grained millstone grit. It is generally light buff in colour with swirls of golden brown / orange giving it a distinct and varied natural appearance. Oxidisation can sometimes occur on the face of the stone causing a dark discolouration.

Longridge Sandstone is cut and profiled for sale to domestic and commercial projects by:
Cumbrian Stone Ltd, Montal Place, Stalker Road, Gilwilly Industrial Estate, Penrith, CA11 9FE.

All stones are cut to order, and generally Longridge Sandstone is available within the following size limitations:

Maximum Length – 2500mm

Maximum Bed Height – 600mm

Minimum Recommended Thickness/Depth – Vertical and Horizontal Applications 40mm

Please note that these limitations can vary depending on the unit sizes required. For all large units it is advisable to contact us to discuss the sizes achievable.

Longridge Sandstone is suitable for most masonry applications, including walling, paving, traditional cladding and architectural features, and can be utilised as a 40mm thin cladding using a kerf and rail/rainscreen cladding system (subject to suitable design).

Technical Performance

All of Cumbrian Stone's products are independently tested in line with British and European Standards via an accredited laboratory. We also carry out in-house consistency testing on a monthly basis in order to assure our customers that our materials will perform as expected once installed.

A copy of our full technical performance data, including our in-house consistency testing, is available for inspection in our offices, and a digital copy of this can be provided on request on a project-by-project basis. Our technical team are also on hand to offer technical advice on the performance and limitations of all of the materials that we produce at Cumbrian Stone.

Please note that as natural stone is a natural product, there can be variations in the composition of the stone that can result in the real-world performance of the stone varying across the raw material. Any technical results provided are an average taken from the testing of multiple samples taken from several quarried blocks as a snapshot of the quarry at that time, and whilst we also carry out consistency checks in our own laboratory on a monthly basis it is not possible to guarantee the real-world performance of every individual stone due to these natural variations. We always advise that natural stone is a self-supporting material rather than a structural component, and Cumbrian Stone would always recommend consulting a structural engineer to establish the minimum required properties where natural stone is being used for structural purposes. We are happy to arrange additional accredited test results for any of our materials on a project-by-project basis (chargeable) should these be required for structural purposes. Due to the natural variations within natural stone, the performance data that we are able to provide is not to be taken as a structural recommendation by Cumbrian Stone in any case.

